



## Declaration of Performance

### FM 744

Anchor heavy 4 sectors made of zinc plated steel

via Trieste, 1 San Giovanni al Natisone  
(UD) Italy - ph. +39 0432 747911  
www.friulsider.com - info@friulsider.com

1. Identification of the product: **FM744**

2. Identification code (art. 11.4), for the batch or serial number see packaging:

d <sup>4)</sup>	L <sup>5)</sup> [mm]	t <sub>fix</sub> <sup>6)</sup> [mm]	Marking	Cod. (only anchor)
M6	40	*	FM-744  M6 Ø10	74400b10040
M8	50	*	FM-744  M8 Ø14	74400b14050
M10	60	*	FM-744  M10 Ø16	74400b16060
M12	80	*	FM-744  M12 Ø20	74400b20080

\* t<sub>fix</sub> = L<sub>screw8.8</sub> - L

d <sup>4)</sup>	L <sup>5)</sup> [mm]	t <sub>fix</sub> <sup>6)</sup> [mm]	Marking	Cod.
M6	40	12	FM-744  M6 Ø10	74411b10040
M8	50	15	FM-744  M8 Ø14	74411b14050
M10	60	20	FM-744  M10 Ø16	74411b16060
M12	80	15	FM-744  M12 Ø20	74411b20080

<sup>4)</sup> Nominal diameter of thread; <sup>5)</sup> Length of anchor; <sup>6)</sup> Thickness fixture max of screw in use.

3. Intended use:

Generic type	Torque controlled expansion anchor sleeve type
Base material	Un-cracked concrete C20/25 to C50/60 acc. to EN 206-1
Material	Steel zinc coated acc. to EN ISO 4042 (screw cl. 8.8 acc. to EN ISO 898-1)
Durability	Internal dry conditions
Loading	Static and quasi-static
Fire Resistance	NPD
Fire Reaction	A1 according to EN 13501-1

4. Manufacturer (art. 11.5): **Friulsider SpA via trieste,1 - 33048 San Giovanni al Natisone (Udine) - Italy**

5. Authorised Representative (art. 12.2): **Not Relevant**

6. System of Assessment AVCP (annex V): **System 1**

7/8. Harmonised Specification & Notified Body:

	Notified Body	System of Assessment	Reference	EN Norm or EAD Document
Technical Specification	CSTB nr.0679	1	<b>ETA-05/0169</b>	<b>ETAG001 p.1-2</b>
Factory Product Control	CSTB nr.0679	1	<b>0679-CPR-0112</b>	

9. Declared Performance: **See Annex**

10. The performance of the product identified in points 1 and 2 is in conformity with declared performance in point 9. This declaration of performance is issued under the sole responsibility of Friulsider SpA.

Signed for and behalf of the manufacturer by:

Name and functions	Place and date of issue	Signature
Sales Manager Fabrizio Fasan	San Giovanni al Natisone, 10-06-2015	

## Annex I°

Declared performances according to ETA-05/0169 - ETAG001 p.1 and 2 Design method ETAG001 Annex C or CEN/TS 1992-4						
ESSENTIAL CHARACTERISTICS			PERFORMANCE			
Installation parameters			M6 <sup>2)</sup>	M8	M10	M12
d <sub>0</sub>	Nominal diameter of drill bit	[mm]	10	14	16	20
h <sub>nom</sub>	Minimum installation depth	[mm]	40	50	60	80
h <sub>ef</sub>	Effective anchorage depth	[mm]	34 <sup>2)</sup>	41	50	67
h <sub>min</sub>	Minimum thickness of the concrete member	[mm]	100	100	100	135
T <sub>inst</sub>	Nominal torque moment	[Nm]	6	15	30	50
s <sub>min</sub>	Minimum spacing	[mm]	35	40	50	70
c <sub>min</sub>	Minimum edge distance	[mm]	35	40	50	70
<b>TENSION Steel failure</b>						
N <sub>Rk,s</sub>	Tension Steel characteristic failure	[kN]	16	29	46	67
γ <sub>ms,N</sub> <sup>1)</sup>	Partial safety factor for tension steel failure	[-]	1,5			
<b>Pull-out failure</b>			M8	M10	M12	M16
N <sub>Rk,p,ucr</sub>	Tension characteristic load in un-cracked concrete C20/25	[kN]	6 <sup>2)</sup>	12	17,8 <sup>3)</sup>	27,3 <sup>3)</sup>
γ <sub>2</sub>	Partial safety factor	[-]	1,0			
γ <sub>mc</sub> <sup>1)</sup>	Partial safety factor	[-]	1,5			
ψ <sub>c C30/37</sub>	Increasing factor for concrete C30/37	[-]	1,22			
ψ <sub>c C40/50</sub>	Increasing factor for concrete C40/50	[-]	1,41			
ψ <sub>c C50/60</sub>	Increasing factor for concrete C50/60	[-]	1,55			
<b>Concrete cone failure and Splitting failure</b>						
K <sub>ucr</sub>	Factor for un-cracked concrete rif. CEN/TS 1992-4-4 §. 6.2.1. 4	[-]	10,1			
s <sub>cr,N</sub>	Critical spacing	[mm]	100	125	150	200
c <sub>cr,N</sub>	Critical edge distance	[mm]	50	62	75	100
s <sub>cr,sp</sub>	Critical spacing (splitting)	[mm]	200	250	300	400
c <sub>cr,sp</sub>	Critical edge distance(splitting)	[mm]	100	125	150	200
γ <sub>mc = γ<sub>m,sp</sub></sub> <sup>1)</sup>	Partial safety factor	[-]	1,5			
<b>Displacement on Tension Load</b>			M8	M10	M12	M16
N <sub>ucr</sub>	Service tension load in un-cracked concrete	[kN]	2,9	5,7	8,5	13,0
δ <sub>NO,ucr</sub>	Short term displacement under tension load	[mm]	0,5	0,6	0,8	1,2
δ <sub>N∞,ucr</sub>	Long term displacement under tension load	[mm]	0,6	0,6	0,8	1,2
<b>SHEAR Steel failure</b>			M8	M10	M12	M16
V <sub>Rk,s</sub>	Shear Steel characteristic failure	[kN]	7,4	14,6	21,5	32,0
K <sub>2</sub>	Ductility factor acc.to CEN/TS 1992-4-5 Section § 6.3.2.1		0,8			
M <sup>0</sup> <sub>Rk,s</sub>	Bending Moment characteristic failure	[Nm]	12	30	60	105
γ <sub>ms,V</sub> <sup>1)</sup>	Partial safety factor for shear steel failure	[-]	1,25			
<b>Shear Concrete Pry-out failure</b>						
k	Factor equation (5.6) of ETAG, Annex C, § 5.2.3.3	[-]	1,0			2,0
k <sub>3</sub>	Factor equation (16) of CEN/TS 1992-4-4, § 6.2.2.3	[-]	1,0			2,0
γ <sub>mc</sub> <sup>1)</sup>	Partial safety factor	[-]	1,5			
<b>Shear Concrete Edge failure</b>						
l <sub>ef</sub>	Effective anchorage length	[mm]	34	41	50	67
d <sub>nom</sub>	Nominal diameter of anchor	[mm]	10	14	16	20
γ <sub>mc</sub> <sup>1)</sup>	Partial safety factor	[-]	1,5			
<b>Displacement on Shear Load</b>			M8	M10	M12	M16
V	Service shear load in concrete	[kN]	4,2	8,3	12,3	18,3
δ <sub>V0</sub>	Short term displacement under shear load	[mm]	2,5	3,3	2,9	3,5
δ <sub>V∞</sub>	Long term displacement under shear load	[mm]	4,5	6,4	5,6	6,8

<sup>1)</sup> In absence of other national regulations; <sup>2)</sup> Use restricted to anchoring of structural components statically indetermined; <sup>3)</sup> Pull-out failure not decisive.

Reach Directive EC 1907/2006 declaration:

We inform you that Friulsider is classified in the EC 1907/2006 Reach Directive as a Downstream-user of substances.

The product supplied does not contain substances classified as SVHC according to the Candidate List in a concentration equal or greater than 0.1% (weight / weight). Article 31 is not applicable to the present product.